



# CHEMPLAX LLC

A KMI Group Company

Technical Data Sheet

## ElastoPrene 85A

### Thermoplastic Vulcanizate (TPV)

#### Product Description

ElastoPrene 85A is a thermoplastic vulcanizate containing an olefin-based rubber and polyolefin resins. It is designed for applications requiring long-term sealing performance, even at elevated temperatures. Soft-touch feel for grips and handles used in automotive and consumer goods. It can be processed using conventional thermoplastic processing equipment that can be extruded or molded into flexible parts. It is an excellent choice for applications requiring flexibility in the following markets → Automotive, Appliance, Business Machines, Construction, Consumer Products, and Electronics.

#### Revision

Revision Date: 2/24/2025

Properties	Method	Value
Density	ASTM D792	0.960g/cm <sup>3</sup>
Melt Flow Rate (230°C/2.16kg)	ASTM D1238	4.74g/10min
Tensile Properties	ASTM D412	
Tensile Strength 100%		6.50 MPa
Tensile Strength		10.0 MPa
Tensile Elongation		490%
Durometer Shore A	ASTM D2240	85

#### Notes

**Processing Parameters:** ElastoPrene material can be processed using conventional thermoplastic processing equipment. Extrusion processing recommendation L/D ratio of 24 or more, and a metering type screw with compression ratio of 3:4.

**For additional inquiries, please contact: [csr.supplychain@kmigroup.com](mailto:csr.supplychain@kmigroup.com)**

TECHNICAL INFORMATION AND DATA REGARDING THE COMPOSITION, PROPERTIES OR USE OF THE PRODUCTS DESCRIBED HERE IS BELIEVED RELIABLE. HOWEVER NO REPRESENTATION OR WARRANTY IS MADE WITH RESPECT THERETO EXCEPT AS MADE BY CHEMPLAX LLC IN WRITING AT TIME OF SALE. CHEMPLAX LLC CANNOT ASSUME RESPONSIBILITY FOR ANY PATENT LIABILITY WHICH MAY RISE FROM THE USE OF ANY PBY CHEMPLAX LLC. RODUCT IN A PROCESS, MANNER OR FORMULA NOT DESIGNED